

Thông tin kỹ thuật

BASIC CLEAR

Danh mục sản phẩm: **C 4**

Dầu bóng Polyurethane cho sơn màu / hệ thống sơn bóng

Lĩnh vực sử dụng

Dầu bóng thích hợp để sử dụng trong tất cả các quá trình sơn sửa lại xe.

Thông tin thêm

Đặc điểm kỹ thuật

Hàm lượng thịt 40 % \pm 2	Tỷ trọng 0.900– 1.000 g/cm ³
Bảo quản ở nhiệt độ Thấp nhất 5°C, cao nhất 45°C	Thời hạn sử dụng 60 tháng

Ứng dụng

Chất nền / Tiền xử lý / Làm sạch

BASIC CLEAR được thiết kế để sử dụng độc nước và sơn màu chịu dung môi.







The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at www.rmpaint.com or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

R-M Automotive Refinish Paints, Z.I. du Merret F-60676 Clermont de l'Oise Cedex, Tel. (+33) (0) 3 44 77 77 77, 12/2014



Thông tin kỹ thuật

BASIC CLEAR

	BASIC CLEAR Chất làm cứng BASIC	100% trên vol. 50% trên vol.
	Độ nhớt ở 20°C: ISO 4 cốc: DIN 4 cốc:	24 đến 26 giây 14 đến 16 giây
	Thời gian sống: 4 giờ ở 20°C	
	Súng áp lực HVLP Súng áp lực phù hợp	1.3 – 1.5 mm 0.7 tại vòi phun 1.3 – 1.4 mm 2.0 – 2.5
	Lớp phun: Độ dày:	2 50 micrômét
	Sấy khô ở 60°C:	30 phút.
	(song ngắn)	8 phút.

Hoàn thiện

Hoàn thiện hoạt động sau thời gian khô quy định và làm mát

Chỉ dẫn an toàn

Nó không thể loại trừ bụi vì sản phẩm có chứa các hạt <0,1 micrômét.

Sản phẩm phù hợp với lĩnh vực chuyên nghiệp.

Khi sử dụng sản phẩm vui lòng tuân thủ các quy định về an toàn và các thiết bị bảo hộ cá nhân