

Thông tin kỹ thuật

CHRONOTOP

Danh mục sản phẩm: **C 4**

Dầu bóng nhanh khô

Lĩnh vực sử dụng

Thích hợp cho sửa chữa nhỏ (phá mí, sơn sửa 1 hoặc 2 tấm thẳng đứng).

Thông tin thêm

Đặc điểm kỹ thuật

Hàm lượng thịt 42 % \pm 2	Tỷ trọng 0.920 – 1.020 g/cm ³
Bảo quản ở nhiệt độ Thấp nhất 5°C, cao nhất 45°C	Thời hạn sử dụng 36 tháng

Ứng dụng

Chú ý: sử dụng **BC 030** chậm và mỏng hơn ở nhiệt độ cao hoặc khi tốc độ không khí cao.

Chất nền / Tiền xử lý / Làm sạch

CHRONOTOP được thiết kế để sử dụng cho sơn màu DIAMONT .







The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at www.rmpaint.com or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

R-M Automotive Refinish Paints, Z.I. du Merret F-60676 Clermont de l'Oise Cedex, Tel. (+33) (0) 3 44 77 77 77, 12/2014



Thông tin kỹ thuật

CHRONOTOP

	CHRONOTOP H 9000 BC 020	100% trên vol. 25% trên vol. 25 – 50% trên vol.	100 g 27 g 23 – 45 g
	Độ nhớt ở 20°C: ISO 4 cốc: DIN 4 cốc:	20 đến 28 giây 14 đến 16 giây	
	Thời gian sống: 4 giờ ở 20°C		
	Súng áp lực HVLP Súng áp lực phù hợp	1.3 – 1.5 mm 1.3 – 1.4 mm	0.7 tại vòi phun 2.0 – 2.5
	Số lớp phun: Độ dày:	2 50 micrômét	
	Sấy khô ở 20°C: Sấy khô ở 60°C:	Không bụi sau 20 phút. Sẵn sàng để lắp ráp lại sau 2 giờ Sửa chữa lại hoàn toàn sau 10 giờ 15 phút.	
	(song ngắn)	8 phút.	

Hoàn thiện

Hoàn thiện hoạt động sau thời gian khô quy định và làm mát.

Chỉ dẫn an toàn

Nó không thể loại trừ bởi vì sản phẩm có chứa các hạt <0,1 micrômét.

Sản phẩm phù hợp với lĩnh vực chuyên nghiệp.

Khi sử dụng sản phẩm vui lòng tuân thủ các quy định về an toàn và các thiết bị bảo hộ cá nhân.