

Thời gian chảy

Đo với các cốc đo độ nhớt khác nhau

D 2

Mô tả quá trình

Tóm tắt các lần chảy đo bằng cốc với lưu lượng khác nhau cho cùng một sản phẩm với cùng độ nhớt ở 20°C.

Chỉ dẫn an toàn

Nó không thể loại trừ bởi vì sản phẩm có chứa các hạt <0,1micrômét.

Sản phẩm phù hợp với lĩnh vực chuyên nghiệp.

Khi sử dụng sản phẩm vui lòng tuân thủ các quy định về an toàn và các thiết bị bảo hộ cá nhân.

ISO 4	BS CUP B4	AFNOR	DIN 4
20	18	15	14
25	20	16	15
30	23	18	16
35	25	20	17
40	26	21	18
45	28	23	19
50	30	24	20
55	33	26	21
60	35	28	23
65	37	29	24
70	39	30	25
75	41	32	26
80	43	34	28
85	45	36	29
90	47	37	30

Các con số ở trên là thời gian dòng chảy đo bằng giây

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at www.rmpaint.com or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

R-M Automotive Refinish Paints, Z.I. du Merret F-60676 Clermont de l'Oise Cedex, Tel. (+33) (0) 3 44 77 77 77, 12/2014

