

# Thông tin kỹ thuật

## D 92

Danh mục sản phẩm: **C 5**

Chất làm cứng Isocyanate để sử dụng ở nhiệt độ cao

### Lĩnh vực sử dụng

Chất làm cứng đặc biệt được thiết kế để sử dụng ở nhiệt độ cao để đảm bảo tất cả các đặc tính của sơn màu và dầu bóng R-M.

### Thông tin thêm

Nó nên được sử dụng ở nhiệt độ trên 30°C sau khi sử dụng dầu bóng: DIAMONTOP MS, STARTOP HS

### Đặc điểm kỹ thuật

Hàm lượng thịt 45 % ± 2	Tỷ trọng 0.930– 1.030 g/cm <sup>3</sup>
Bảo quản ở nhiệt độ Thấp nhất 5°C, cao nhất 45°C	Thời hạn sử dụng 24 tháng

### Ứng dụng

Khuấy đều trước khi dùng.

### Chất nền / Tiền xử lý / Làm sạch

Theo quy định trong bảng dữ liệu của sản phẩm, trong đó D92 đang được sử dụng.






The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at [www.rmpaint.com](http://www.rmpaint.com) or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

R-M Automotive Refinish Paints, Z.I. du Merret F-60676 Clermont de l'Oise Cedex, Tel. (+33) (0) 3 44 77 77 77, 12/2014



# Thông tin kỹ thuật

## D 92

	<b>DIAMONTOP MS</b> <b>D 92</b>	100% trên vol. 40% trên vol.	100 g 43 g
	<b>STARTOP HS</b> <b>D 92</b> <b>BC 020, BC 030</b>	100% trên vol. 50% trên vol. 15% trên vol.	100 g 52 g 14 g
	<b>Potlife:</b> 7 giờ ở 20°C		
	Theo quy định trong bảng dữ liệu của sản phẩm, trong đó D92 đang được sử dụng.		
	Theo quy định trong bảng dữ liệu của sản phẩm, trong đó D92 đang được sử dụng.		
	Sấy khô với 20°C: Sấy khô với 60°C:	24 giờ 30 phút.	

### Hoàn thiện

Panel được hoàn thiện có thể bao phủ lại hoặc thiết lập lại sau khi sấy khô hoặc yêu cầu làm mát..

### Chỉ dẫn an toàn

Nó không thể loại trừ bởi vì sản phẩm có chứa các hạt <0,1micrômét.

Sản phẩm phù hợp với lĩnh vực chuyên nghiệp.

Khi sử dụng sản phẩm vui lòng tuân thủ các quy định về an toàn và các thiết bị bảo hộ cá nhân.