

Thông tin kỹ thuật

PUR BLACK DIAMONT

Danh mục sản phẩm: **C 3.2**

Sơn màu Jet Black

Lĩnh vực sử dụng

Sơn màu Jet black dùng để hoàn thiện sửa chữa ô tô

Thông tin thêm

Đặc điểm kỹ thuật

| | |
|--|---|
| Hàm lượng thịt 25 % ± 2 | Tỷ trọng 0.870 – 0.970 g/cm ³ |
| Bảo quản ở nhiệt độ Thấp nhất 5°C, cao nhất 45° | Thời hạn sử dụng 24 tháng |

Ứng dụng

Khuấy đều trước khi dùng

Trộn mới phải được khuấy bằng tay trước khi sử dụng và thêm 15 phút trộn với máy. Khuấy tất cả các sản phẩm được lưu trữ trong máy trộn 2 lần mỗi ngày trong 15 phút.

Chất nền/ tiền xử lý/ làm sạch

Làm sạch với PK 700 hoặc PK 2000.

Mài với P400 (mài liền đầy hoặc sửa chữa khô, sơn cũ dung môi ổn định).

Làm sạch với PK 700 hoặc PK 2000.

Thay thế: áp dụng liền R-M ướt trên ướt hoặc chất cách nhiệt

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at www.rmpaint.com or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.






R-M Automotive Refinish Paints, Z.I. du Merret F-60676 Clermont de l'Oise Cedex, Tel. (+33) (0) 3 44 77 77 77, 12/2014

Perfection made simple



Thông tin kỹ thuật

PUR BLACK DIAMONT

| | | | |
|--|---|---------------------------------|-------------------------------|
|  | DIAMONT D 403 BC 020 | 100% trên vol. 60% trên vol. | 100 g 53 g |
|  | Độ nhớt ở 20°C: ISO 4 cốc: DIN 4 cốc: | 40 giây 18 giây | |
| | Thời gian sống: | 24 giờ ở 20°C | |
|  | Súng áp lực HVLP Súng áp lực phù hợp | 1.3 – 1.5 mm 1.3 – 1.4 mm | 0.7 tại vòi phun 2.0 – 2.5 |
|  | Số lớp phun: Độ dày: | 2 20 micrômét | |
|  | Sấy khô ở 20°C | 15 phút. | |

Hoàn thiện

Sau thời gian nghỉ, áp dụng đầu bóng R-M ướt trên ướt.

Chỉ dẫn an toàn

Nó không thể loại trừ bởi vì sản phẩm có chứa các hạt <0,1 micrômét.

Sản phẩm phù hợp với lĩnh vực chuyên nghiệp.

Khi sử dụng sản phẩm vui lòng tuân thủ các quy định về an toàn và các thiết bị bảo hộ cá nhân.