

Thông tin kỹ thuật

SEALER PLAST 80

Danh mục sản phẩm: **C 2.3**

Sơn lót bám dính cho nhựa

Lĩnh vực sử dụng

SEALER PLAST 80 là sơn lót bám dính cho nhựa.

Thông tin thêm

Nó đảm bảo độ bám dính tốt của lớp sau (liền đây, sơn màu).

Đặc điểm kỹ thuật

Hàm lượng thịt 7 % ± 2	Tỷ trọng 0.840–0.940 g/cm ³
Bảo quản ở nhiệt độ Thấp nhất 5°C, cao nhất 45°C	Thời hạn sử dụng 24 tháng

Ứng dụng

Khuấy đều trước khi dùng. SEALER PLAST 80 luôn sẵn sàng để sử dụng.

Chất nền / Tiền xử lý / làm sạch

Quan trọng: nhiệt dẻo hoàn thiện phải loại bỏ.





The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at www.rmpaint.com or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

R-M Automotive Refinish Paints, Z.I. du Merret F-60676 Clermont de l'Oise Cedex, Tel. (+33) (0) 3 44 77 77 77, 12/2014



Thông tin kỹ thuật

SEALER PLAST 80

	Độ nhót ở 20°C: ISO 4 cốc: 14 giây DIN 4 cốc: 13 giây
	Thời gian sống: không giới hạn trong hộp kín.
	Súng áp lực HVLP 1.3 mm 0.7 tại vòi phun Súng áp lực phù hợp 1.3 – 1.4 mm 2.0 bar
	Số lớp phun: 1 – 2 Độ dày: Khoảng 10 micrômét
	Thời gian nghỉ ở 20°C 15 phút.

Hoàn thiện

Áp dụng liên tiếp PU R-M 2K ướt trên ướt. Dùng SEALER PLAST 80 một lần nữa khi thời gian chờ vượt quá 30 phút ở 20° C

Chỉ dẫn an toàn

Nó không thể loại trừ bởi vì sản phẩm có chứa các hạt <0,1 micrômét.

Sản phẩm phù hợp với lĩnh vực chuyên nghiệp.

Khi sử dụng sản phẩm vui lòng tuân thủ các quy định về an toàn và các thiết bị bảo hộ cá nhân.